

	FICHE TECHNIQUE	VB87	IE : 03
	CARTON BLANC BOIS COUCHE	févr.-05	Page 1/1

GRAMMAGE	EPAISSEUR	MAIN	HUMIDITE	RIGIDITE TABER (Gr*F*Cm)	
				GR/M ²	MICRONS
250	305	1,22	6.5	70	24
270	340	1,26	6.5	85	31
280	350	1,25	6.5	100	36
290	360	1,24	6.5	115	38
300	375	1,25	7	125	40
310	387	1,25	7	140	45
320	400	1,25	7	150	50
330	410	1,24	7	155	55
340	420	1,24	7	165	65
350	430	1,23	7	175	70
360	445	1,24	7	190	75
370	455	1,23	7	205	80
380	470	1,24	7	225	85
400	490	1,23	7	255	95
420	520	1,24	7	270	110
430	530	1,23	7	285	120
450	550	1,22	7	315	135
480	580	1,21	7	360	155
500	605	1,21	7	405	170
520	635	1,22	7	425	185
550	665	1,21	7	485	205
600	730	1,22	7.5	555	235

BLANCHEUR : 80

TOLERANCES :

Grammage	+/- 5 %	Blancheur	+/- 4
Epaisseur	+/- 5 %	Rigidité	- 15 %
Humidité	+/- 1	Longueur	+/- 2 mm
Main	+/- 5 %	Equerrage	+/- 1 mm