



## FICHE TECHNIQUE

VB97

IE : 02

CARTON BLANC BOIS COUCHE

Février-05

Page 1/1

GRAMMAGE	EPAISSEUR	Humidité	MAIN	RIGIDITE TABER (Gr*F*Cm)	
Gr/m <sup>2</sup>	Microns	%	Cm <sup>3</sup> /Gr	Sens marche	Sens travers
<b>250</b>	<b>313</b>	<b>6,5</b>	<b>1,25</b>	<b>70</b>	<b>25</b>
<b>270</b>	<b>340</b>	<b>6,5</b>	<b>1,26</b>	<b>90</b>	<b>32</b>
<b>280</b>	<b>354</b>	<b>6,5</b>	<b>1,26</b>	<b>105</b>	<b>38</b>
<b>290</b>	<b>365</b>	<b>6,5</b>	<b>1,26</b>	<b>115</b>	<b>42</b>
<b>300</b>	<b>378</b>	<b>6,5</b>	<b>1,26</b>	<b>125</b>	<b>44</b>
<b>310</b>	<b>390</b>	<b>7</b>	<b>1,26</b>	<b>135</b>	<b>54</b>
<b>320</b>	<b>405</b>	<b>7</b>	<b>1,27</b>	<b>150</b>	<b>60</b>
<b>330</b>	<b>420</b>	<b>7</b>	<b>1,27</b>	<b>160</b>	<b>65</b>
<b>340</b>	<b>432</b>	<b>7</b>	<b>1,27</b>	<b>170</b>	<b>70</b>
<b>350</b>	<b>445</b>	<b>7</b>	<b>1,27</b>	<b>200</b>	<b>80</b>
<b>360</b>	<b>458</b>	<b>7</b>	<b>1,27</b>	<b>210</b>	<b>85</b>
<b>370</b>	<b>470</b>	<b>7</b>	<b>1,27</b>	<b>220</b>	<b>90</b>
<b>380</b>	<b>483</b>	<b>7</b>	<b>1,27</b>	<b>235</b>	<b>95</b>
<b>400</b>	<b>508</b>	<b>7</b>	<b>1,27</b>	<b>260</b>	<b>105</b>
<b>420</b>	<b>535</b>	<b>7</b>	<b>1,27</b>	<b>280</b>	<b>110</b>
<b>430</b>	<b>545</b>	<b>7</b>	<b>1,27</b>	<b>310</b>	<b>125</b>
<b>450</b>	<b>570</b>	<b>7</b>	<b>1,27</b>	<b>340</b>	<b>135</b>
<b>480</b>	<b>610</b>	<b>7</b>	<b>1,27</b>	<b>400</b>	<b>150</b>
<b>500</b>	<b>635</b>	<b>7</b>	<b>1,27</b>	<b>420</b>	<b>165</b>
<b>550</b>	<b>700</b>	<b>7</b>	<b>1,27</b>	<b>470</b>	<b>197</b>
<b>600</b>	<b>760</b>	<b>7,5</b>	<b>1,27</b>	<b>570</b>	<b>240</b>

BLANCHEUR : 80%

TOLERANCES :

<b>Grammage</b>	+/- 5 %	<b>Blancheur</b>	+/- 2
<b>Epaisseur</b>	+/- 5 %	<b>Rigidité</b>	- 15 %
<b>Humidité</b>	+/- 1	<b>Longueur</b>	+/- 2 mm
<b>Main</b>	+/- 5 %	<b>Equerrage</b>	+/- 1 mm