

**FICHE TECHNIQUE**

VG97

IE : 02

CARTON BLANC GRIS COUCHE

14-02-05

Page 1/1

GRAMMAGE	EPAISSEUR	Humidité	MAIN	RIGIDITE TABER (Gr*F*Cm)	
				Sens marche	Sens travers
Gr/m ²	Microns	%	Cm ³ /Gr		
250	313	6,5	1,25	70	25
270	340	6,5	1,26	90	32
280	354	6,5	1,26	105	38
290	365	6,5	1,26	115	42
300	378	6,5	1,26	125	44
310	390	7	1,26	135	54
320	405	7	1,27	150	60
330	420	7	1,27	160	65
340	432	7	1,27	170	70
350	445	7	1,27	200	80
360	458	7	1,27	210	85
370	470	7	1,27	220	90
380	483	7	1,27	235	95
400	508	7	1,27	260	105
420	535	7	1,27	280	110
430	545	7	1,27	310	125
450	570	7	1,27	340	135
480	610	7	1,27	400	150
500	635	7	1,27	420	165
550	700	7	1,27	470	197
600	760	7,5	1,27	570	240

BLANCHEUR : 80%

TOLERANCES :

Grammage	+/- 5 %	Blancheur	+/- 2 %
Epaisseur	+/- 5 %	Rigidité	- 15 %
Humidité	+/- 1 %	Longueur	+/- 2 mm
Main	+/- 5 %	Equerrage	+/- 1 mm